


// POWERBLADE HP™ 2.0



TEST	UNIT	SPECIFICATIONS
Linear Density - Denier*	Denier	10,800
Thickness	Microns	240
Break Strength**	lbs/force	20
Elongation	%	> 30
Total Lead Content	ppm	< 100
Total Product Weight***	oz / yd ²	68
Pile Yarn Fiber Weight****	oz / yd ²	40
Primary Backing Weight****	oz / yd ²	8
Secondary Backing Weight†	oz / yd ²	20
Average Pile Height****	inches	2.0
Average Tuft Bind Strength	lb / force	> 10
Tufting Gauge	inches	1/2
Average Grab Tear Strength	lb / force	> 200
g-Max		< 200
Pill Flammability		Pass
Infiltrometer (Drainage)	in / hr	> 25

Except where noted as a minimum or maximum, the above specifications are nominal.

* All values are ± 8% ** All values are ± 25% *** All values are ± 10% **** All values are ± 5% † All values are ± 3 oz



The colors shown are not intended for exact matching purposes, please refer to actual sample swatches for accurate hues.